



Coim S.p.A

20019 SETTIMO MILANESE -ITALIA
VIA MANZONI,28/32
TEL.02 33505.1
TELEFAX 02 3286415-33505250

TECHNICAL DATA SHEET

LARIPUR 8520

THERMOPLASTIC POLYURETHANE

Specific gravity	gr/cm ³	1.22	(DIN 53479)
Shore hardness	A	86	(DIN 53505)
Abrasion loss	mm ³	35	(DIN 53516)
Tensile Modulus	50% N/mm ²	5.7	(DIN 53504)
	100% "	7.4	"
	300% "	14.7	"
Tensile strength	N/mm ²	48.0	(DIN53504)
Elongation at break	%	580	(DIN 53504)
Tear strength	N/mm	86	(DIN 53515)
Vicat Softening Poin	°C	86	(ISO 306)
Compression Set	70h/23°C	21	(DIN53517)
	22h/70°C	43	"
	70h/100°C	"	"

Transparent, EEC and FDA food contact approved.

Note: The present technical note has been written basing on our best knowledge but is not released as a specification for the above mentioned materials.

The international standards here indicated to be intended as a reference to carry out the various but the choice of available options and any possible variation are mentioned in our respective internal standards.

